This item is the archived peer-reviewed author-version of:

Diamond microelectrode arrays for in vitro neuronal recordings

Reference:

McDonald Matthew , Monaco Antonina, Vahidpour Farnoosh, Haenen Ken, Giugliano Michele, Nesladek Milos.- Diamond microelectrode arrays for in vitro neuronal recordings

MRS Communications - ISSN 2159-6859 - 7:3(2017), p. 683-690

Full text (Publisher's DOI): <https://doi.org/10.1557/MRC.2017.62>

To cite this reference: <http://hdl.handle.net/10067/1458290151162165141>

Diamond microelectrode arrays for in-vitro neuronal recordings

Matthew McDonald¹, Antonina Monaco², Farnoosh Vahidpour¹, Ken Haenen¹, Michele Giugliano^{2,3}, and Milos Nesladek^{1,4}

1 Institute of Materials Research, Hasselt University, 3590, Diepenbeek, Belgium

2 Department of Biomedical Sciences, University of Antwerp, B-2610, Wilrijk, Belgium

3 Brain Mind Institute, Swiss Federal Institute of Technology Lausanne, Switzerland; and Dept. Computer Science, University of Sheffield, S1 4DP, UK

4 Interuniversity Microelectronics Center (IMEC), B-3001, Heverlee, Belgium

Keywords: Nano-crystalline diamond, Microelectrode arrays, Neuronal recordings, Impedance spectroscopy

Contact Information:

Matthew McDonald: Email: mattmcd87@gmail.com, Phone: +1 604 500-3124

Antonina Monaco: Email: antonina.monaco@uantwerpen.be, Phone: +32-3-2652488

Abstract

A novel microfabrication technique for micro-electrode arrays (MEAs) with a full diamond-cell interface is demonstrated. Boron-doped nano-crystalline diamond is used as a conductive electrode material on metal tracks insulated by intrinsic nano-crystalline diamond (NCD). MEAs successfully recorded spontaneous electrical activity in rat primary cortical neuronal cultures. Patch-clamp measurements show no alterations to cell membrane passive properties or active firing response, for cell developing *ex vivo* on diamond. Impedance analysis revealed low impedance magnitude of BNCD electrodes, suitable for multi-unit neuronal recordings. Additionally, the impedance phase of the fabricated electrodes shows a high degree of capacitive coupling, ideal for neuron stimulation.

Introduction

Diamond has become a material of increasing interest for electronic devices over the last decade, particularly as a biological sensing platform, due to its many attractive material properties¹. Nano-crystalline diamond (NCD) thin films can be grown by chemical vapour deposition (CVD) on various substrates to fabricate functional devices using standard microfabrication techniques. Diamond is a wide band gap semiconductor that can be doped to give metal-like conductivity, allowing development of biocompatible electrodes which are electrochemically robust, giving an extremely wide chemical potential window². Furthermore, the wide bandgap of un-doped diamond allows it to be used as an insulating material in the voltage range of biological signals.

Microelectrode arrays (MEAs) were developed in the 1970s, and have become an indispensable tool in the field of electrophysiology for non-invasively investigating electrical activity of excitable cells, such as neurons and cardiomyocytes, both *in vivo* and *in vitro*. Moreover, MEAs enable the recording of spontaneous extracellular electric signals, allowing the interactions within populations of synaptically connected neurons to be studied, including their collective response to drugs, crucial for therapeutic drug-screening. MEAs can also be used to directly stimulate neurons, in order to study evoked response and the underlying networks organization, connectivity, and response dynamics³. However, most of the MEAs show both the capacitive and injection currents. The injection currents, depending on the current used, may deteriorate the neural tissue due to the local pH changes. The capacitive current is of high interest due to absence of any non-displacement currents.

Here we report on the fabrication of MEAs using boron-doped nano-crystalline diamond (BNCD) microelectrodes with a passivation layer made of intrinsic nano-crystalline diamond. BNCD exhibits many advantages as an electrode material compared to common gold, platinum and TiN materials, including high chemical and mechanical stability, a 3V-wide electrochemical water potential window, and high biocompatibility^{4,5}. Moreover, BNCD has been shown to be an effective electrode material for biological sensors⁵⁻⁹. NCD is also highly biocompatible^{4,10}, as

well as transparent, and insulating, making it a suitable material as a passivation layer to provide a complete diamond sensing platform surface. Recently, full diamond MEAs were used for detection of action potential of myocardial cells which generally have substantially higher amplitudes than for neurons⁶. One of the limits of such technology is the high resistance of the electrodes. Our work led to electrodes with purely capacitive coupling and resistance comparable to the state of the art non-diamond MEAs. Our method of fabrication combined with optimal layout and specific diamond surface functionalization allowed for extracellular recording of neural signals from hippocampal neurons.

Materials and Methods

Design and fabrication of MEAs

The MEA design was derived from commercial planar MEAs (MultiChannel System GmbH, Reutlingen, Germany) to allow comparison of performance with commercial MEAs. It incorporates a regular 8x8 arrangement of 40µm diameter circular microelectrodes with a pitch of 200µm, as shown in figure 1. Figure 2 shows the fabrication process for the MEA, which starts with a wafer of size 49mm made from quartz glass in order to withstand the stresses induced from high temperature diamond growth. The fabrication technique has the advantage of using a single photolithographic step to open the electrodes in the insulating NCD layer and grow the conductive BNCD layer; this allows for the insulating and conductive layers to be at the same level, with virtually no step height between them. Additionally, the MEAs are made on a transparent quartz substrate so that neurons are easily visualized using standard microscopy.

Quartz substrates were initially prepared by standard RCA 1 and RCA 2 cleaning¹¹. Metal tracks were defined on the substrate using standard photolithography lift-off techniques. A thin (~5nm) titanium adhesion layer was sputtered, followed by 300nm gold and a second (~20nm) adhesion layer of titanium. The surface was seeded for diamond growth by spin coating a 0.33 g/L solution of detonation diamond nanoparticles on the substrate (NanoAmando[®]B, NanoCarbo Research Institute, Japan)¹². The NCD passivation layer was then grown using a gas mixture of 3% methane and 97% hydrogen in a MPECVD (Microwave Plasma Enhanced Chemical Vapor Deposition) growth reactor (Seki Technotron corp. AX6500). NCD was grown at a plasma temperature of 600-650°C, by maintaining a pressure of 15Torr and 2000W with total gas flow of 300sccm. A second lift-off process was used to sputter a hard mask of aluminum nitride (AlN) which defined the electrode area. Oxygen reactive ion etching (RIE) was used to open holes in the passivation layer and expose titanium/gold electrodes below. The substrate was then selectively seeded with detonation diamond nanoparticles, which attached to the electrode while being repelled by the surface charge of AlN¹². BNCD electrodes were then grown with a gas mixture of hydrogen, methane and trimethylboron (TMB) in a MPECVD growth reactor (Seki Technotron corp. AX6500). BNCD was grown at plasma temperature of 750°C at 30Torr and 3500W with total gas flow of 500sccm. Finally, the contacts were opened by placing a silicon wafer over the center area and etching the diamond covering the electrodes with an oxygen plasma treatment.

Additionally, a set of 1cm x 1cm NCD coated quartz substrates were prepared to test if the fabrication procedure left any artefacts that could have negative effects on the electrophysiological properties of the cells. Substrates went through all the same fabrication steps as MEAs, except for metal track deposition or photolithography to define microelectrode-opening holes.

Rat primary cortical neurons cultures

Prior to cell seeding, BNCD-MEAs and commercial ITO-based glass MEAs (Multichannel Systems GmbH), employed as control, were treated with 70% ethanol for 10 minutes and air-dried overnight. Quartz substrates and glass coverslips used for patch clamp experiment were autoclaved upon high-pressure saturated steam at 121°C for 30 min. MEAs, substrates and coverslips were then coated with Polyethylenimine (PEI) by incubation under 0.1% w/v of PEI in milli-Q water at room temperature for at least 8h; samples were then rinsed thoroughly with milli-Q water and air dried^{4,13}. The PEI treatment is based on our previous results, in which we demonstrated the PEI or Poly-D-lysine is necessary pre-condition for vital neuron growth¹³.

Rat primary cortical cultures were obtained by postnatal (P0) Wistar rats (Charles River, France) using standard methods and following the guidelines of the Ethics Committee of the University of Antwerp. Cortices were dissected, sliced, digested in a trypsin solution, mechanically dissociated, centrifuged and suspended in Modified Essential Medium supplemented with 5% horse serum, 50µg/mL gentamycin, 200mM l-glutamine and 2M glucose.

Cells were seeded at nominal densities of 6500cells/mm² on MEAs, and of 1500cells/mm² on glass coverslips and quartz substrates. All chemicals were purchased by Sigma Aldrich (Belgium).

Electrophysiology

Cellular electrophysiology

Whole-cell patch-clamp recordings were carried out at 34°C from neuronal somas after 9 Days in Vitro (DIV) using an Axon Multiclamp Amplifier (Molecular Devices, USA) controlled by LCG software¹⁴. During recordings, glass coverslips and BNCD-coated quartz substrates were kept in artificial cerebrospinal fluid, containing (in mM): 145 NaCl, 5 Hepes, 5 Glucose, 4 KCl, 2 CaCl₂, 2 Na-pyruvate and 1 MgCl₂; pH adjusted to 7.4 with NaOH.

Patch pipettes were pulled from borosilicate glass and filled with intracellular solution, containing (in mM): 135 K-gluconate, 10 Hepes, 10 PC-Na₂, 4 NaCl, 4 ATP-Mg²⁺, 0.3 GTP-Na₂ and 0.2 EGTA; pH adjusted to 7.3 with KOH. Electrical impedance of patch pipettes was 6-8 MΩ. Recordings were analysed using custom MATLAB scripts (The Math-works, USA). Statistical analysis was performed using the Liliefors test, to assess normality of data sets, and the Student's t-test to evaluate statistical significance; data are presented as mean ± standard error of the mean (SEM).

Network electrophysiology

Neuronal network activity was recorded at 17, 19, 21, 24 and 28 DIV from 2 control ITO-MEAs and 7 BNCD-MEAs, mounted into a recording amplifier (Multichannel System GmbH). Spontaneous electrical activity was recorded for 30 min; traces were acquired and stored on disk for offline analysis by MCRack (Multichannel Systems, Germany) and subsequently analysed by QSpoke Tools¹⁵.

Individual microelectrodes of a MEA were defined as active, when the frequency of occurrence of detected biological events (spikes) at that single electrode exceeded 0.05 Hz.

Results and Discussion

Morphological characterization

Important characteristics of functional MEA electrodes are the impedance and capacitance. These parameters depend on the material and geometrical properties used for the construction of the functional electrodes as well as for the isolating layer. Diamond has the advantage of being able to be used both as a conductive and an isolating material. While undoped diamond is highly isolating, the conducting diamond is obtained by p-type doping with boron. The thickness of the doped and undoped diamond layers determines the capacitive and isolating properties respectively. The thickness of the diamond layers is also important from the fabrication point of view, for definition of the lithographic and etching steps. The thickness of diamond passivation layer was therefore carefully monitored by in-situ interferometry and was optimised to approximately 180nm, which was sufficient to insulate the metal tracks. BNCD electrodes, were between 180-200nm, which was found by using profilometry to measure the step height above the diamond passivation layer. The average electrode diameter was approximately 30 μm , giving an active area of $\sim 707\mu\text{m}^2$. Scanning electron microscopy was used to measure the morphology and grain-size of the diamond layers. NCD and BNCD crystals are highly faceted, with an average grain size of $\sim 100\text{nm}$ and $\sim 200\text{nm}$, respectively (figure 3).

The grain size is an important parameter for obtaining an optimal diamond film surface in terms of crystal quality (and consequently good electrical properties) and surface roughness of the electrode surface. Consequently, the grain size was controlled by the growth parameters such as the methane concentration in the gas mixtures during growth. A concentration of 3% methane was used for the NCD growth to provide a smoother continuous film with low stress, to ensure no pinholes or cracking in the layer¹⁶. A methane concentration of 1% was used in the gas mixture for BNCD to obtain a larger diamond grain size in order to maximize the conductivity¹⁷. A boron to carbon ratio of 9,000ppm in the gas mixture was used to ensure sufficient boron doping levels for high electrode conductivity. The resultant layers had conductivities of ca. 400 Ω /square.

Electrochemical characterization

One of the critical requirements for microelectrodes to detect multi-unit neuronal activity is to have a low enough impedance in the frequency range of 0.1-1kHz, enabling adequate spatial selectivity and sensitivity¹⁸. Impedance of BNCD electrodes is expressed in terms of the equivalent Randles circuit and depends on the BNCD impedance (doping and the electrode geometry) as well as on forming the electric charge double layer on the electrode immersed in bio-analyte. To simulate the working conditions, impedance spectroscopy (IS) was used to perform the electrical characterization of the devices prior to cell seeding. IS was performed in 1M phosphate buffer in frequency sweep mode with 0.1V peak to peak sine wave from 1MHz to 1Hz (Solartron SI1260 Impedance/Gain Analyzer). Electrodes show typical shape and characteristics of diamond electrodes¹⁹; with impedance values around 300k Ω at 1kHz (figure 4). The lowest obtained impedance was ~100 k Ω for electrodes with 30 μ m diameter active area (identical to commercial MEAs). Interestingly, IS showed -80° to -90° phase angle, in the range of 100-10,000Hz (figure 5), which shows an almost completely capacitive coupling of the electrical current, ideal for the stimulation of cells²⁰. Most electrode materials, such as gold²¹, ITO²², or carbon nanotubes²³, have a charge injection behaviour that is a combination of Faradic and capacitive currents. When MEAs are used for stimulation, charge injection through Faradic currents can result in damage to the surrounding cell tissues²¹. Diamond is a highly inert material which has a large electrochemical window (~3eV) and low double-layer capacitance (ca. 7 μ F/cm²), resulting in an almost perfect capacitive charge injection²⁴. The capacitive coupling is ideal in terms of the neural interfaces stability as no active ionic, i.e. Faradic currents flow between the cell membrane and the electrode, which would otherwise impact on electrochemical degradation of the cell tissue.

Additionally, impedances of all MEAs were tested at 1kHz using an impedance testing device MEA-IT (Multichannel Systems GmbH). Impedance values were measured before and after attachment of a glass ring with a PDMS-based glue (Sylgard 184, Dow Corning) for creating a culture chamber on the MEA. Figure 5a,b shows the impedance magnitude and phase for all of the 59 electrodes on a representative MEA, showing that the average impedance increases drastically after exposure to PDMS, while the average phase stays relatively constant. The average impedance value for each MEA in the set, before and after ring attachment, is reported in figure 5c. Though the standard ring mounting procedure was followed, using a PDMS based elastomer, impedance dramatically increased, and reaching values up to 1250 K Ω . Reasons for this increase might lie in the fact that PDMS has been known to outgas monomers that can diffuse across the substrate surface and significantly impact electrode performance^{25,26}. Diamond surface is extremely sensitive on forming a strong bond to charged molecules or polymers²⁷ that might lead to formation of an isolating layer on the surface, leading to impedance enhancement. Though the thickness of the polymer layer can be reduced significantly by liquid chemistry, the last monolayer of polymer is strongly bound chemically to diamond surface and practically irremovable by for example, stripping in liquid SDS. Partial electrode performance was recovered by performing a cleaning in CF₄ plasma to try to remove PDMS residues²⁸. This procedure led to a lower electrode impedance, though still higher when compared to those of MEAs before ring attachment.

Cellular electrophysiology and Functional tests

In order to assess whether NCD affects neuronal viability, single-cell, or network's properties, whole-cell patch clamps recordings were performed under the voltage-clamp configuration on neurons grown on NCD substrates. Results (figure 6) show that neurons grown on NCD substrates have membrane passive properties (i.e., time constant, input resistance, and membrane potential) and active response firing properties comparable to control conditions (n=6 cells).

Functional tests

To devise functionality of MEAs, a set of experiments is currently undergoing with the diamond MEAs, involving the extracellular recording and stimulation of rat primary cortical neuronal cultures. Preliminary results indicate that BNCD electrodes, with NCD passivation layer, can detect single spikes and bursts with amplitudes in the 20-30 μV range with noise levels of ca. $\pm 6 \mu\text{V}$ (See figure 7). Comparison among the functional BNCD channels to ITO reference electrodes shows similar noise levels, as well as similar spike amplitudes, though ITO references performed slightly better, however ITO electrodes are a mix of capacitive and resistive Faradic behaviour²². ITO references electrodes showed amplitudes in the range of 40-50 μV with a noise level of ca. $\pm 6 \mu\text{V}$. Furthermore, it appears that spike detection may be better on the reference electrodes, though further analysis is required to determine whether this is due to lower spike detection, or a physiological change due to the diamond surface. We attribute this result to the high impedance caused by the PDMS during ring attachment, leading to a lower spike amplitude and lower spike detection, rather than any change to the network function. The electrode resistance rises up from ~ 400 to ~ 1250 Ohms after the ring attachment. After CF_4 plasma cleaning, the resistance decreased to ~ 800 Ohms. Currently we are developing plasma technologies to remove the polymer monolayers from the diamond surface without any re-deposition of etched organic molecules to the surface.

While diamond has continuously been shown to be a good substrate for neuron growth⁴, we have demonstrated here that it can also be used as an effective isolation layer at thicknesses of $< 180\text{nm}$. This allows the cell culture to be in direct contact with only one material minimising any contact potential as well as provides homogenous neuron coverage. This property is important for studying neural networks as it is known that neural growth is strongly dependent on the material on which the neural cultures are cultivated²⁹. PEI is a polymer commonly used in the pretreatment of glass for cell culturing as it adds surface charges that promote neural adhesion. Poly-L-lysine (PEI) was also used as a pretreatment to cell culturing on diamond MEAs as it was found to also promote strong neural adhesion and growth on NCD substrates⁴.

Furthermore, we show that it is possible to fabricate MEAs on optically transparent substrates and produce highly homogenous layers with negligible leakage current from cracks or pinholes. Our new fabrication process has been designed to allow a variable height of the electrode

compared to the isolation layer, from $\sim 100\text{nm}$ below to $> 1\mu\text{m}$ above. An electrode height close to the thickness level of the passivation layer minimized the cleft size between the cell and device. This improves coupling when the cell is tightly bound to the passivation layer, by bringing the electrode as close to the cell as possible. A greater signal-to-noise ratio (SNR) should be possible by resolving the issue of increased impedance from gluing glass rings to the MEA and a strategy for this is being developed. The impedance could further be improved by using nanostructuring techniques to increase the surface area; this could easily be added into the current fabrication process with no additional lithography step needed³⁰. Recently we have already achieved $\sim 10\times$ increase of the BNCD capacitance, making it attractive for ultrasensitive MEAs based on purely capacitive coupling⁷. In summary, this fabrication process can be used to make functional MEAs from a fully diamond interface on transparent substrates for neural recordings that perform similarly to ITO reference MEAs; with room in the process to enhance the electrode interface.

In conclusion, we have developed a novel fabrication for MEAs made of thin diamond films on transparent substrates, which allow detection of neural signals with advantage of diamond biocompatibility, surface neutrality, capacitive coupling and excellent electrochemical characteristics.

Acknowledgements

Financial support from the FP7 of the European Commission (NMP project “MERIDIAN” n. 280778-02, IEF “INCA-NANEP” n. 328214, ITN “NAMASEN” n. 264872), the Flanders Research Foundation (FWO, contract n. G088812N) is acknowledged. We also thank Mr. D. Van Dyck and Mr. M. Wijnants for technical assistance.

References

1. C. E. Nebel, B. Rezek, D. Shin, H. Uetsuka, and N. Yang: Diamond for bio-sensor applications. *J. Phys. D. Appl. Phys.* **40**(20), 6443 (2007).
2. A. Kraft, G. GmbH, and K. Str: Doped Diamond : A Compact Review on a New , Versatile Electrode Material. *Int. J. Electrochem. Sci.* **2**, 355 (2007).
3. A. Stett, U. Egert, E. Guenther, F. Hofmann, T. Meyer, W. Nisch, and H. Haemmerle: Biological application of microelectrode arrays in drug discovery and basic research. *Anal. Bioanal. Chem.* **377**(3), 486 (2003).
4. A. Vaitkuvienė, M. McDonald, F. Vahidpour, J.-P. Noben, K. Sanen, M. Ameloot, V. Ratautaite, V. Kaseta, G. Biziuleviciene, A. Ramanaviciene, M. Nesladek, and A. Ramanavicius: Impact of differently modified nanocrystalline diamond on the growth of neuroblastoma cells. *N. Biotechnol.* **32**(1), 7 (2015).
5. M. Cottance, S. Nazeer, L. Rousseau, G. Lissorgues, A. Bongrain, R. Kiran, E. Scorsone, P. Bergonzo, A. Bendali, S. Picaud, and S. Joucla: Diamond Micro-Electrode Arrays (MEAs): a new route for in-vitro applications . *DTIP* No. April, 16 (2013).
6. V. Maybeck, R. Edgington, A. Bongrain, J. O. Welch, E. Scorsone, P. Bergonzo, R. B.

- Jackman, and A. Offenhäusser: Boron-Doped Nanocrystalline Diamond Microelectrode Arrays Monitor Cardiac Action Potentials. *Adv. Healthc. Mater.* **3**(2), 283 (2014).
7. M. Alcaide, A. Taylor, M. Fjorback, V. Zachar, and C. P. Pennisi: Boron-Doped Nanocrystalline Diamond Electrodes for Neural Interfaces : In vivo Biocompatibility Evaluation. **10**(March), 1 (2016).
 8. M. McDonald, D. Croux, F. Vahidpour, L. Curley, P. Pobedinskas, K. Haenen, M. Giugliano, Z. Vl, L. Kavan, M. Nesl, I. For, and S. Sio: All-diamond functional surface micro-electrode arrays for brain-slice neural analysis. *Phys. Status Solidi A* **214**(2) (2017).
 9. E. M. Hudak, D. W. Kumsa, H. B. Martin, D. J. Garrett, K. Ganesan, A. Stacey, A. R. Harris, S. J. Morgan, and J. Chen: Conducting polymer coated neural recording electrodes Biofouling resistance of boron-doped diamond neural stimulation electrodes is superior to titanium nitride electrodes in vivo. (n.d.).
 10. R. J. Edgington, a Thalhammer, J. O. Welch, a Bongrain, P. Bergonzo, E. Scorsone, R. B. Jackman, and R. Schoepfer: Patterned neuronal networks using nanodiamonds and the effect of varying nanodiamond properties on neuronal adhesion and outgrowth. *J. Neural Eng.* **10**(5), 56022 (2013).
 11. W. Kern: The Evolution of Silicon Wafer Cleaning Technology. **137**(6), 7 (1990).
 12. P. Pobedinskas, G. Degutis, W. Dexters, W. Janssen, S. D. Janssens, B. Conings, B. Ruttens, J. D'Haen, H.-G. Boyen, a. Hardy, M. K. Van Bael, and K. Haenen: Surface plasma pretreatment for enhanced diamond nucleation on AlN. *Appl. Phys. Lett.* **102**(20), 201609 (2013).
 13. S. M. Ojovan, M. McDonald, N. Rabieh, N. Shmuel, H. Erez, M. Nesladek, and M. E. Spira: Nanocrystalline diamond surfaces for adhesion and growth of primary neurons, conflicting results and rational explanation. *Front. Neuroeng.* **7**(June), 1 (2014).
 14. D. Linaro, J. Couto, and M. Giugliano: Command-line cellular electrophysiology for conventional and real-time closed-loop experiments. *J. Neurosci. Methods* **230**, 5 (2014).
 15. M. Mahmud, R. Pulizzi, E. Vasilaki, and M. Giugliano: QSpoke tools: a generic framework for parallel batch preprocessing of extracellular neuronal signals recorded by substrate microelectrode arrays. *Front. Neuroinform.* **8**(March), 26 (2014).
 16. T. Vandevelde, M. Nesladek, C. Quaeys, and L. Stals: Optical emission spectroscopy of the plasma during CVD diamond growth with nitrogen addition. *Thin Solid Films* **290–291**, 143 (1996).
 17. S. D. Janssens, P. Pobedinskas, J. Vacik, V. Petráková, B. Ruttens, J. D'Haen, M. Nesládek, K. Haenen, and P. Wagner: Separation of intra- and intergranular magnetotransport properties in nanocrystalline diamond films on the metallic side of the metal-insulator transition. *New J. Phys.* **13** (2011).
 18. D. R. Merrill and P. A. Tresco: Impedance Characterization of Microarray Recording Electrodes in Vitro. *IEEE Trans Biomed Eng* **52**(11), 1960 (2005).
 19. K. Honda, T. N. Rao, D. A. Tryk, A. Fujishima, M. Watanabe, K. Yasui, and H. Masuda: Electrochemical Characterization of the Nanoporous Honeycomb Diamond Electrode as an Electrical Double-Layer Capacitor. *J. Electrochem. Soc.* **147**(2), 659 (2000).

20. P. Fromherz and A. Stett: Silicon-Neuron Junction: Capacitive Stimulation of an Individual Neuron on a Silicon Chip. *Phys. Rev. Lett.* **21** **75**(8), 1670 (1995).
21. S. F. Cogan, K. A. Ludwig, C. G. Welle, Y. H. Kim, G. H. Kim, A. Y. Kim, and Y. H. Han: Tissue damage thresholds during therapeutic electrical stimulation In vitro extracellular recording and stimulation performance of nanoporous gold-modified multi-electrode arrays. (n.d.).
22. F. O. Morin, Y. Takamura, and E. Tamiya: Investigating neuronal activity with planar microelectrode arrays: achievements and new perspectives. *J. Biosci. Bioeng.* **100**(2), 131 (2005).
23. R. Gerwig, K. Fuchsberger, B. Schroepel, G. S. Link, G. Heusel, U. Kraushaar, W. Schuhmann, A. Stett, and M. Stelzle: PEDOT – CNT composite microelectrodes for recording and electrostimulation applications : fabrication , morphology , and electrical properties. **5**(May), 1 (2012).
24. O. Frank, V. Petrk, and H. Tarbkov: Electrochemistry and in situ Raman spectroelectrochemistry of low and high quality boron doped diamond layers in aqueous electrolyte solution. *Electrochimica Acta* **87**, 518 (2013).
25. K. J. Regehr, M. Domenech, J. T. Koepsel, K. C. Carver, J. Ellison-zelski, W. L. Murphy, L. A. Schuler, E. T. Alarid, and J. David: Biological implications of polydimethylsiloxane-based microfluidic cell culture. *Lab Chip.* **9**(15), 2132 (2009).
26. Nagarah and J. Michael: Planar Silicon Patch-Clamp Electrodes Integrated with Polydimethylsiloxane Microfluidics (ProQuest, 2009).
27. H. Krysova, Z. Vlckova-Zivcova, J. Barton, V. Petrk, M. Nesladek, P. Cigler, and L. Kavan: Visible-light sensitization of boron-doped nanocrystalline diamond through non-covalent surface modification. *Pccp* **17**(2), 1165 (2015).
28. J. Garra, T. Long, J. Currie, T. Schneider, R. White, and M. Paranjape: Dry etching of polydimethylsiloxane for microfluidic systems. *J. Vac. Sci. Technol. A Vacuum, Surfaces, Film.* **20**(3), 975 (2002).
29. P. Fattahi, G. Yang, G. Kim, and M. R. Abidian: A Review of Organic and Inorganic Biomaterials for Neural Interfaces. *Adv. Mater.* **26**(12), 1846 (2014).
30. G. Piret, C. Hbert, J.-P. Mazellier, L. Rousseau, E. Scorsone, M. Cottance, G. Lissorgues, M. O. Heuschkel, S. Picaud, P. Bergonzo, and B. Yvert: 3D-nanostructured boron-doped diamond for microelectrode array neural interfacing. *Biomaterials* **53**, 173 (2015).

Figure Legend

Fig. 1 Fully packaged BNCD/NCD MEA (left) and SEM image of the active sensing area (right).

Fig. 2 Fabrication process of MEAs with BNCD electrodes and NCD passivation layer. a) a Ti/Au/Ti metal tri-layer is deposited using lift-off photolithography to form the metal tracks, b) the surface is seeded with diamond nanoparticles and 180nm NCD layer is grown by MPECVD,

c) photolithography is used to define a hard mask made of AlN, d) the NCD layer is etched through to the underlying metal track by oxygen plasma, e) the surface is selectively seeded with diamond nanoparticles and the BNCD electrode is grown, f) AlN is etched in a KOH solution.

Fig. 3 SEM image of BNCD electrode (left) and SEM image showing fine grain structure of BNCD electrode vs. NCD passivation layer.

Fig. 4 Bode plot of a BNCD electrode with active area of $707\mu\text{m}^2$. Insert shows the frequency-phase response of the electrode.

Fig. 5 a) Plot of impedance magnitude and phase of all microelectrodes before and after b) attaching a glass ring as a culture chamber. c) Impedance magnitudes for 5 MEAs, averaged over all their microelectrodes.

Fig. 6 Effect on neurons cell properties by culturing on BNCD films compared to control condition (n=6). a) time constant τ , b) membrane resting potential E, c) input resistance R, d) action potential rate. Error bars correspond to standard deviation of the data.

Fig. 7 Spiking activity recorded on a diamond MEA compared to a control MEA with ITO electrodes.

Fig. 1 Fully packaged BNCD/NCD MEA (left) and SEM image of the active sensing area (right).

238x117mm (150 x 150 DPI)

Fig. 2 Fabrication process of MEAs with BNCD electrodes and NCD passivation layer.

130x154mm (150 x 150 DPI)

Fig. 3 SEM image of BNCD electrode (left) and SEM image showing fine grain structure of BNCD electrode vs. NCD passivation layer.

237x102mm (150 x 150 DPI)

Fig. 4 Bode plot of a BNCD electrode with active area or $707\mu\text{m}^2$. Insert shows the frequency-phase response of the electrode.

202x180mm (72 x 72 DPI)

Fig. 5 a) Plot of impedance magnitude and phase of all microelectrodes before and after b) attaching a glass ring as a culture chamber. c) Impedance magnitudes for 5 MEAs, averaged over all their microelectrodes.

192x175mm (150 x 150 DPI)

Figure 6 Growing neurons on BNCD film does not affect single-cell passive (time constant τ , membrane resting potential E , input resistance R) and excitable properties (Action Potential Rate) when compared to control condition ($n = 6$).

224x137mm (150 x 150 DPI)

Fig. 7 Spiking activity recorded on a diamond MEA compared to a control MEA with ITO electrodes.

231x100mm (150 x 150 DPI)